



Silicone Technologies, LLC

359 Hill Street, Biddeford, ME 04005 •
Tel: (207) 283-6422 • Fax: (207) 283-6551
www.crisil-silicones.com

ISO 9001:2000 Certified

CRI-SIL Silicone Technologies, LLC
359 Hill Street
Biddeford, Maine 04005
(207) 283-6422

PRODUCT

CSB435

Product Description

CRI-SIL HCR Silicone Rubber CSB435 is an un-catalyzed 35 durometer high strength base. Following are typical results when using 0.15 pph DBPH peroxide.

Press Cured

10 min @ 350°F

Properties

Typical Results

Plasticity	-	152
Specific Gravity		1.10
Durometer (Shore A)		35
Tensile psi		1105
Elongation %		1035
100% Modulus		108
Tear B		162

These values are not to be used to set specifications. Each user must evaluate this product for his or her intended use. All information is given in good faith, without warranty, representation, inducement or a license of any kind. CRI-SIL does not assume any legal responsibility for use of or reliance upon same. No warranty or representation is given that CRI-SIL products described will be suitable in buyers and or users formulations or processes for any particular end use. No representation is given as to freedom from patent infringement. Materials not manufactured or supplied by CRI-SIL may present hazards in handling and use. Contact supplier or the manufacturer for all information specific to this these matters